

AKSAD GROUP PETROCHEM

PVC

S-75

Type	Value
Appearance	W.P.*
Inherent Viscosity	0.67 - 0.72
K-Value	56 - 58
Practice Size	Nil
% Retained on 40 Mesh	=> 85
% Retained on 200 Mesh	
Porosity (ML/GR)	0.05 – 0.2
Valatile Matter	0.7
(Heart Loss) %Max	
Bulk Density(GR/CC)	0.5 - 0.62
(apparent)	
Dark Resin	0.10
(Per 10SQ.IN.)	